

WETHERTEX

HD77



HD77
Pliolite Heavy Texture Coating
High Polymer

Technical Data

Pack Size
25kg Drum

Pack Size
30 Units

Finishing Tool
R1 Roller

Suitable Substrate
Suitable WetherTex™ Primer / Base Coat

Water Down
Max 2% - with S62 Diluter

Coverage
10 M² per unit

Application Temperature
1 °c - 25 °c

Humidity Requirement
Less than 95%





Long Term Protection
& Low Maintenance



Water Repellent



High Adhesion



Low Temperature
Application



Roller
Application



Highly
Polymer Modified

A high performance trowel & roll pliolite based anti-crack through coloured flexible heavy textured coating, can be applied in lower temperatures.

PRODUCT INFORMATION

HD77 Pliolite Heavy Texture Coating is a premium quality, long life high build coating formulated for exterior use on cement rendering and concrete surfaces. It provides a self-stabilizing textured matt finish that has excellent adhesion to previously painted and porous surfaces.

PREPARATION

On new base coat HD77 Pliolite Heavy Texture Coating can be applied directly to a suitably prepared substrate. For re-furbishment projects, make good cracks and structural defects and remove any loose flaking and brittle material. If there is evidence of organic growth, power wash to remove & apply WetherTex Fungicidal wash in accordance with instructions. Then ensure that the substrate has been primed or base coated with a suitable product for the substrate type. Beads and expansion joints should be included as required by the substrate and BS standards and carried through all applied materials.

Any further technical advice is available on request.

PRIMING

Suitable WetherTex Primer or Base Coat.

MIXING

HD77 Pliolite Heavy Texture Coating is supplied ready to use, but may need re-mixing using a suitable paddle mixer to regain correct consistency for application.

**HD77**

Note: HD77 may stiffen on standing. Re-mix the product to regain a workable consistency but do not add more than 5% S62 Diluter.

APPLICATION

To avoid dampness and discoloration application should be avoided below DPC or within 150mm of ground level.

Trowel - Apply smoothly and evenly to a thickness of about 1.5 - 2.5mm, with the help of a steel trowel. To create the texture - Load a lamb's wool roller generously and apply with minimum pressure in short slow strokes covering small areas at a time. Move the roller from top to bottom, left to right or right to left to create desired effect.

Specification Clauses relating to this product can be found in NBS Section M20 Rendering. BS 5262 Code of Practice for External Rendering and BS 8000-10 must be followed.

STORAGE

When stored unopened in a dry place at temperatures above 5°C, shelf life is 12 months from date of manufacture.

TOOL CLEANING

All equipment must be washed with clean water immediately after use. Waste material should not be emptied into drainage systems.

HEALTH & SAFETY INSTRUCTIONS

For further information, please request the material safety data sheet for this product.

IMPORTANT INFORMATION

The weather conditions for application and drying are critical. Do not apply if any of the following conditions are likely to arise during - or in the first 24 hours following application:

- o If frost is forecast, or in excessive wet conditions
- o When Relative Humidity is above 95%
- o In temperatures below +1°C or above +25°C
- o If the elevation is in direct sunlight
- o If the substrate is hot (at or above 30C) or below +1°C
- o Coverage rates are approx. and do not take into account wastage and uneven substrates

To the best of our knowledge and belief, this information is true and accurate. However, as conditions of use of the product and the expertise of any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application if no spec has been provided for the project in hand. No responsibility can be accepted, nor any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.