

WETHERTEX

MP44



MP44
Pliolite Spray Coating
High Polymer

Technical Data

Pack Size
25kg Drum

Pallet QTY
30 Units

Finishing Tool
Spray unit

Suitable Substrate
Suitable WetherTex™ primer / Base Coat

Water Down
Max 2% - with S62 Diluter

Coverage
10 - 20 M² per unit dependant on substrate

Application Temperature
1 °c - 25 °c

Humidity Requirement
Less than 95%





Long Term Protection & Low Maintenance



Water Repellent



High Adhesion



Low Temperature Application



Suitable for Spray Application



Highly Polymer Modified

A high performance spray applied pliolute based anti-crack through coloured flexible spotted textured coating, can be applied in lower temperatures.

PRODUCT INFORMATION

MP44 Pliolite Spray Coating is a premium quality, long life spray applied coating formulated for exterior use on cement rendering and concrete surfaces. It provides a self-stabilizing textured matt finish that has excellent adhesion to previously painted and porous surfaces.

PREPARATION

On new, clean, dry sound surfaces MP44 Pliolite Spray Coating can be applied directly to a suitably prepared substrate. For re-furbishment projects. Remove all loose and flaking materials. Make good cracks and structural defects. All surfaces must be reasonably dry and free from algae, lichen & other growths and grease. If there is evidence of organic growth, power wash to remove & apply WetherTex Fungicidal wash in accordance with manufacturers instructions.

PRIMING

PP1 Prep-Wash Primer

MIXING

MP44 Pliolite Spray Coating is supplied ready to use, but may need re-mixing using a suitable paddle mixer to regain correct consistency for application.

Note: MP44 may stiffen on standing. Re-mix the product to regain a workable consistency but do not add more than 5% S62 Diluter.



FM 54357

MP44

APPLICATION

To avoid dampness and discoloration application should be avoided below DPC or within 150mm of ground level.

Apply using suitable spray equipment. Spray gun tip should be held at a suitable distance from the wall to avoid overloading of material and "bounce back". Hold spray gun at right angles to wall at all times. Use either horizontal or vertical motions and overlap on each pass of the gun by 30% to ensure even appearance. Avoid heavy build-up of material when overlapping. To avoid overlapping marks, a wet edge should always be maintained, avoid starting and stopping midway on a wall, continue to spray until a natural break, such as a downpipe or corner is reached.

Specification Clauses relating to this product can be found in NBS Section M20 Rendering. BS 5262 Code of Practice for External Rendering and BS 8000-10 must be followed.

STORAGE

When stored unopened in a dry place at temperatures above 5°C, shelf life is 12 months from date of manufacture.

TOOL CLEANING

All equipment must be washed with clean white spirit or an alternative solvent cleaning agent, immediately after use. Waste material should not be emptied in the drainage systems. Some local authorities have special facilities for the disposal of leftover paint. Please do not add any product into drains or watercourses.

HEALTH & SAFETY INSTRUCTIONS

For further information, please request the material safety data sheet for this product.

IMPORTANT INFORMATION

The weather conditions for application and drying are critical. Do not apply if any of the following conditions are likely to arise during - or in the first 24 hours following application:

- o If frost is forecast, or in excessive wet conditions
- o When Relative Humidity is above 95%
- o In temperatures below +1°C or above +25°C
- o If the elevation is in direct sunlight
- o If the substrate is hot (at or above 30C) or below +1°C
- o Coverage rates are approx. and do not take into account wastage and uneven substrates

To the best of our knowledge and belief, this information is true and accurate. However, as conditions of use of the product and the expertise of any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application if no spec has been provided for the project in hand. No responsibility can be accepted, nor any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.